

What is claimed is:

1. An organic fiber filler-containing polypropylene resin composition comprising a polypropylene resin satisfying the following equation and an organic fiber filler in a proportion of 1 to 250 parts by weight of the filler per 100 parts by weight of the resin composition:

$$\log MT > 4.24 \times \log [\eta] - 1.2 \quad (1)$$

wherein MT represents a melt tension (unit: cN) of the polypropylene resin at 230°C, and  $[\eta]$  represents an intrinsic viscosity (unit: dl/g) of the polypropylene resin measured in tetralin at 135°C.

2. The organic fiber filler-containing polypropylene resin composition as described in claim 1, wherein the polypropylene resin is an olefin polymer composition (A) described below or a mixture comprising the above olefin polymer composition (A) and a polypropylene base resin (B) described below, and a mixing proportion of the above polypropylene base resin (B) is 90 % by weight or less based on the mixture:

the olefin polymer composition (A): an olefin polymer composition comprising (a) and (b) described below:

(a) 0.01 to 5.0 parts by weight of polyethylene which is an ethylene homopolymer or an ethylene-olefin copolymer having an ethylene polymer unit of 50 % by weight or more and which has an intrinsic viscosity  $[\eta_E]$  falling in a range of 15 to 100 dl/g measured in tetralin at 135°C, and

(b) 100 parts by weight of polypropylene which comprises a propylene homopolymer or a propylene-olefin copolymer having a

propylene polymer unit of 50 % by weight or more and which has a  
intrinsic viscosity  $[\eta]$  of 0.2 to 10 dl/g measured in tetralin  
at 135°C; and

the polypropylene base resin (B): a propylene homopolymer or a  
5 propylene/ $\alpha$ -olefin copolymer comprising propylene as a principal  
component.

3. The organic fiber filler-containing polypropylene resin  
composition as described in claim 1, further comprising a foaming  
10 agent.

4. The organic fiber filler-containing polypropylene resin  
composition as described in claim 2, further comprising a foaming  
agent.  
15

5. A molded article obtained by extrusion- molding the organic  
fiber filler-containing polypropylene resin composition as  
described in claim 1.

20 6. A molded article obtained by extrusion-molding the organic  
fiber filler-containing polypropylene resin composition as  
described in claim 2.

7. A molded article obtained by extrusion-molding the organic  
fiber filler-containing polypropylene resin composition as  
25 described in claim 3.

8. A molded article obtained by extrusion-molding the organic  
fiber filler-containing polypropylene resin composition as

described in claim 4.

10053425.044702